

SOLID WOOD WORKTOPS

TECHNICAL SPECIFICATION SHEET

THICKNESS

Worktops are 40mm thick; tolerances are within +/- 0.3mm

SIZE

The dimensions are 4100mm x 650mm /3050mm x 900mm/3050mmx650mm

QUALITY

The quality is A (top side) / B (underside)

CONSTRUCTION

Finger-jointing solid wood staves make up the board

STAVES

The staves are within a width range of 38mm to 41mm

CALIBRATION

Sanding of A side is made with 120 grit sander belts; a fully automated sanding line is used

GLUE

The glue used is in accordance with EN 204 D3 and is formaldehyde free.

MOISTURE CONTENT

The moisture content during production, is within 8% and 10%

PACKAGING

All tops are individually stretch-wrapped. A full pallet consists of a quantity of 20 tops. Boards are available individually, no minimum quantity applies.

DENSITY

The average density of our solid wood worktops is 750kg per m³

STORAGE RECOMMENDATIONS

Store in racks with maximum 500mm gaps
Store in humidity between 40% and 55% and in normal room temperature of 18°C and 23°C